

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 0 779 335 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:
12.12.2001 Bulletin 2001/50

(51) Int Cl.7: **C08L 27/16**, C09D 127/16,
C08L 51/06, C09D 151/06,
C08F 214/22, C08F 216/14

(21) Application number: **95929219.4**

(86) International application number:
PCT/JP95/01679

(22) Date of filing: **23.08.1995**

(87) International publication number:
WO 96/06887 (07.03.1996 Gazette 1996/11)

(54) **AQUEOUS DISPERSION OF VINYLIDENE FLUORIDE COPOLYMER AND AQUEOUS
DISPERSION OF VINYLIDENE FLUORIDE SEED POLYMER**

WÄSSRIGE DISPERSION VON VINYLIDENFLUORID-COPOLYMER UND WÄSSRIGE
DISPERSION VON VINYLIDENFLUORID-KORNPOLYMER

DISPERSION AQUEUSE DE COPOLYMERES DE FLUORURE DE VINYLIDENE ET DISPERSION
AQUEUSE DE POLYMERES SOUCHE DE FLUORURE DE VINYLIDENE

(84) Designated Contracting States:
DE FR GB IT

(30) Priority: **31.08.1994 JP 20735994**

(43) Date of publication of application:
18.06.1997 Bulletin 1997/25

(73) Proprietor: **DAIKIN INDUSTRIES, LIMITED**
Osaka-shi Osaka 530 (JP)

(72) Inventors:
• **TSUDA, Nobuhiko**
1-1, Nishihitotsuya Settsu-shi Osaka 566 (JP)
• **IWAKIRI, Ryuzi**
1-1, Nishihitotsuya Settsu-shi Osaka 566 (JP)
• **YONEI, Yasushi Yodogawa-seisakusho**
Settsu-shi Osaka 566 (JP)
• **IMOTO, Katsuhiko Yodogawa-seisakusho**
Settsu-shi Osaka 566 (JP)
• **SHIMIZU, Yoshiki Yodogawa-seisakusho**
Settsu-shi Osaka 566 (JP)

• **ARAKI, Takayuki Yodogawa-seisakusho**
Settsu-shi Osaka 566 (JP)
• **KONDO, Masahiro Yodogawa-seisakusho**
Settsu-shi Osaka 566 (JP)

(74) Representative: **Tiedtke, Harro, Dipl.-Ing.**
Patentanwaltsbüro
Tiedtke-Bühling-Kinne & Partner
Bavariaring 4
80336 München (DE)

(56) References cited:
EP-A- 0 041 735 EP-A- 0 360 575
EP-A- 0 748 826 JP-A- 2 132 101
JP-A- 4 325 509 JP-B- 2 016 326
JP-B- 2 048 579

• **PATENT ABSTRACTS OF JAPAN** vol. 004, no.
061 (C-009), 8 May 1980 & JP 55 029519 A (ASAHI
GLASS CO LTD), 1 March 1980, & JP 61 033 848 B

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 0 779 335 B1

Description


TECHNICAL FIELD

5 [0001] The present invention relates to an aqueous dispersion of a vinylidene fluoride copolymer, and an aqueous dispersion of a vinylidene fluoride seed polymer. The above-mentioned aqueous dispersion of a vinylidene fluoride copolymer and aqueous dispersion of a vinylidene fluoride seed polymer are used suitably, for example, for paints for aqueous coating.

10 BACKGROUND ART

[0002] Hitherto fluorine-containing paints being excellent in water resistance and weather resistance have been used as paints for various buildings. However, many of the above-mentioned fluorine-containing paints are of organic solvent type, and fluorine-containing paints of aqueous type have been required from safety and environmental protection points of view. Many proposals have been made as to aqueous dispersion of a fluorine-containing polymer which is a base component of fluorine-containing paints of aqueous type and as to processes for preparation thereof.

15 [0003] For instance, in JP-B-33848/1986 there is described a process for preparing an aqueous dispersion of a fluorine-containing elastomer made of vinylidene fluoride-tetrafluoroethylene-hexafluoropropylene, which has a particle size of 0.02 μm , in the presence of a fluorine-containing surfactant which has a polymerizable double bond and is represented by



wherein n is an integer of 1 to 7, M is an amine or an alkali metal. However, though there is obtained an aqueous dispersion containing small particles, since the content of the dispersed elastomer is not more than 25 % by weight, the obtained aqueous dispersion is insufficient as one for an aqueous paint because a thickening effect by a thickener is not enough. Further there is no description as to stability of the elastomer-dispersed particles when the solid content is increased and also as to the use for an aqueous paint.


30 [0004] JP-B-55441/1992 discloses a process for emulsion-polymerizing an ethylenically unsaturated monomer in the presence of fluorine-containing polymer particles in an aqueous medium, and JP-A-7784/1991 discloses a process for emulsion-polymerizing an ethylenically unsaturated monomer in the presence of vinylidene fluoride copolymer particles in an aqueous medium. Those patent publications describe seed polymerization of an acrylic monomer, but there is no description therein as to controlling the size of seed particles used for seed polymerization and as to use for seed polymerization of seed particles prepared by employing a reactive emulsifying agent. When seed particles of not more than 50 nm are used, problems arise, since the viscosity of the obtained aqueous dispersion becomes high, the aqueous dispersion having a high solid content cannot be obtained and coagulation occurs when the aqueous dispersion is used under high shear force.

35 [0005] Also JP-B-4396/1975 discloses a process for preparing an acrylic emulsion system wherein a microemulsion having an average particle size of not more than 50 nm is prepared by copolymerizing with acrylic acid at the copolymerization and then neutralizing the produced emulsion with ammonia. In the polymerization of fluorine-containing olefin, particularly vinylidene fluoride monomer, if a non-fluorine-containing carboxylic acid monomer such as acrylic acid is present, the polymerization is inhibited remarkably. Therefore, no polymerization of a fluorine-containing olefin has been made actually in such a system.


40 [0006] In JP-B-17858/1974, there is disclosed a process for copolymerizing a linear saturated fluorine-containing elastic resin with a fluorine-containing vinyl compound having -COOH group on its side chain in order to introduce crosslinkable groups into the elastic resin, but there is no description as to an aqueous dispersion, control of particle size of particles in the aqueous dispersion and an aqueous paint.

45 [0007] In "Kobunshi Ronbunshu" Vol. 36, No. 11, pp. 729-737 (1979), there is disclosed that when a large amount of various surfactants is used in emulsion polymerization, particles of a polymer become smaller, and that even if a mixture of an anionic surfactant and a nonionic surfactant is used in polymerization of an acrylic monomer, the same effect as in case of using an anionic surfactant can be obtained. However if a large amount of such surfactants is used, adverse effects arise such that when a coating film is formed with an emulsion paint, precipitation of the surfactant occurs and that water resistance of the coating film is lowered.

50 [0008] In JP-B-79249/1993, JP-B-85575/1993 and JP-A-255222/1993, there is disclosed that a compound of the formula



5



10 wherein n is an integer, Y is SO_3M or COOM (M is an amine salt or an alkali metal), X is F or CF_3 , or the like is copolymerized with tetrafluoroethylene, and the obtained copolymer is used as an ion-exchange membrane. In those patent publications, there are examples of solution polymerization to obtain the ion-exchange membrane, but there is neither an example of emulsion polymerization in an aqueous medium nor a disclosure of an aqueous paint.

15 [0009] EP-A-0 360 575 discloses vinylidene fluoride polymers used as seed particles in emulsion-polymerization. An aqueous fluorine-containing polymer dispersion is obtainable by reacting 5 to 95 parts by weight of a monomer mixture consisting of at least one monomer selected from alkyl acrylates and alkyl methacrylates and optionally an ethylenically unsaturated compound copolymerizable with the alkyl acrylates and the alkyl methacrylates in an aqueous medium in the presence of 100 parts by weight of particles of a vinylidene fluoride polymer. The particle size of this seed vinylidene fluoride polymer falls in the range of from 0.05 to 3 μm . According to one example of this disclosure 20 a vinylidene fluoride polymer dispersion is prepared having a solid content of 60 % and an average particle diameter of 0.27 μm .

[0010] EP-A-0 041 735 discloses fluorine polymers having acid functionality. The polymerization of vinylidene fluoride with ethylenically unsaturated perfluorinated surface active compounds is described. These fluorine polymers are useful as ion exchange membranes in electrolytic cells.

25 [0011] An object of the present invention is to provide an aqueous dispersion of a vinylidene fluoride copolymer being excellent in stability against sedimentation and having a high solid content of 30 to 60 % by weight in the aqueous dispersion and a small average particle size of the copolymer of not more than 200 nm; an aqueous dispersion of a vinylidene fluoride seed polymer having a small average particle size of the seed polymer of not more than 250 nm and a high solid content of 30 to 60 % by weight of the seed polymer; and processes of preparation thereof. These 30 dispersions are suitable to endow aqueous paints prepared by employing each aqueous dispersion with water resistance, weather resistance, chemical resistance and highly glossy film forming property.

DISCLOSURE OF THE INVENTION

35 [0012] The present invention relates to an aqueous dispersion of a vinylidene fluoride copolymer, characterized in that the dispersion has a solid content of 30 to 60 % by weight and an average particle size of the copolymer of not more than 200 nm; the copolymer being prepared by copolymerizing vinylidene fluoride monomer with at least one reactive emulsifying agent selected from the group consisting of those represented by the formula (I):

40



45 wherein a is an integer of 1 to 10, Y is SO_3M or COOM (M is H, NH_4 or an alkali metal), the formula (II):

50




wherein X is F or CF_3 , b is an integer of 1 to 5, Y is SO_3M or COOM (M is H, NH_4 or an alkali metal), the formula (III):


55




wherein X is F or CF₃, c is an integer of 1 to 10, Y is SO₃M or COOM (M is H, NH₄ or an alkali metal), the formula (IV):



wherein X is F or CF₃, d is an integer of 1 to 10, Y is SO₃M or COOM (M is H, NH₄ or an alkali metal), the formula (V):




wherein e is 0 or an integer of 1 to 10, Y is SO₃M or COOM (M is H, NH₄ or an alkali metal), and the formula (VI):



wherein f is an integer of 1 to 10, Y is SO₃M or COOM (M is H, NH₄ or an alkali metal).

[0013] Further the present invention relates to an aqueous dispersion of a vinylidene fluoride seed polymer prepared by emulsion-polymerizing an ethylenically unsaturated monomer in the presence of vinylidene fluoride copolymer particles, characterized in that the vinylidene fluoride copolymer is a copolymer prepared by copolymerizing vinylidene fluoride monomer with at least one reactive emulsifying agent selected from the group consisting of those represented by the formula (I):




wherein a is an integer of 1 to 10, Y is SO₃M or COOM (M is H, NH₄ or an alkali metal), the formula (II):




wherein X is F or CF₃, b is an integer of 1 to 5, Y is SO₃M or COOM (M is H, NH₄ or an alkali metal), the formula (III):




wherein X is F or CF₃, c is an integer of 1 to 10, Y is SO₃M or COOM (M is H, NH₄ or an alkali metal), the formula (IV):



wherein X is F or CF₃, d is an integer of 1 to 10, Y is SO₃M or COOM (M is H, NH₄ or an alkali metal), the formula (V):



wherein e is 0 or an integer of 1 to 10, Y is SO_3M or COOM (M is H, NH_4 or an alkali metal), and the formula (VI):



wherein f is an integer of 1 to 10, Y is SO_3M or COOM (M is H, NH_4 or an alkali metal), and that the dispersion has a solid content of 30 to 60 % by weight and an average particle size of the seed copolymer of not more than 250 nm.

Description of the Preferred Embodiments of the Invention

[0014] The aqueous dispersion of the vinylidene fluoride copolymer of the present invention is an aqueous dispersion of a vinylidene fluoride (VdF) copolymer obtained from VdF monomer and a reactive emulsifying agent.

[0015] The above-mentioned reactive emulsifying agent is a fluorine-containing compound having a polymerizable C=C double bond and a hydrophilic group in its molecule, and is at least one compound selected from the group consisting of those represented by the formula (I):




wherein a is an integer of 1 to 10, Y is SO_3M or COOM (M is H, NH_4 or an alkali metal), the formula (II):




wherein X is F or CF_3 , b is an integer of 1 to 5, Y is SO_3M or COOM (M is H, NH_4 or an alkali metal), the formula (III):




wherein X is F or CF_3 , c is an integer of 1 to 10, Y is SO_3M or COOM (M is H, NH_4 or an alkali metal), the formula (IV):



wherein X is F or CF_3 , d is an integer of 1 to 10, Y is SO_3M or COOM (M is H, NH_4 or an alkali metal), the formula (V):



wherein e is 0 or an integer of 1 to 10, Y is SO_3M or COOM (M is H, NH_4 or an alkali metal), and the formula (VI):






wherein f is an integer of 1 to 10, Y is SO_3M or COOM (M is H, NH_4 or an alkali metal).

[0016] In the above-mentioned formula (I), it is preferable that a is an integer of 1 to 5 from the viewpoint of surface activating ability of the reactive emulsifying agent, that Y is COOM from the viewpoint of stability of the compound and that M is H or NH_4 from the viewpoint of water resistance of a coating film.


[0017] Examples of the compound represented by the above-mentioned formula (I) are, for instance, $\text{CF}_2=\text{CF}-\text{CF}_2-\text{COONH}_4$, $\text{CF}_2=\text{CF}-\text{CF}_2-\text{COOH}$, $\text{CF}_2=\text{CF}-\text{CF}_2\text{CF}_2\text{COOH}$, $\text{CF}_2=\text{CF}-\text{CF}_2-\text{COONa}$, $\text{CF}_2=\text{CF}-\text{CF}_2-\text{SO}_3\text{NH}_4$, $\text{CF}_2=\text{CF}-\text{CF}_2-\text{SO}_3\text{H}$, $\text{CF}_2=\text{CF}-\text{CF}_2\text{CF}_2\text{SO}_3\text{H}$ and $\text{CF}_2=\text{CF}-\text{CF}_2\text{CF}_2\text{SO}_3\text{Na}$. $\text{CF}_2=\text{CFCF}_2\text{COONH}_4$ is preferable from the viewpoint that an aqueous dispersion of a VdF copolymer having a small particle size can be obtained at a high concentration.

[0018] In the above-mentioned formula (II), it is preferable that X is CF_3 from the viewpoint of stability of the compound, that b is an integer of 1 to 3 from the viewpoint of surface activating ability of the reactive emulsifying agent, that Y is COOM or SO_3M from the viewpoint of stability of the compound and that M is H or NH_4 from the viewpoint of water resistance of a coating film.

[0019] Examples of the compound represented by the above-mentioned formula (II) are, for instance,



and



[0020] From the viewpoint that an aqueous dispersion of a VdF copolymer having a small particle size can be obtained,



is preferable.

[0021] In the above-mentioned formula (III), it is preferable that X is F or CF₃ from the viewpoint of stability of the compound and weather resistance, that c is an integer of 1 to 5 from the viewpoint of surface activating ability of the reactive emulsifying agent, that Y is COOM or SO₃M from the viewpoint of stability of the compound and that M is H or NH₄ from the viewpoint of water resistance of a coating film.

[0022] Examples of the compound represented by the above-mentioned formula (III) are, for instance, CF₂=CF-OCF₂CF₂CF₂COOH, CF₂=CF-OCF₂CF₂COONH₄ and CF₂=CF-OCF₂COOH. CF₂=CF-OCF₂CF₂CF₂COOH is preferable from the viewpoint that an aqueous dispersion of a VdF copolymer having a small particle size can be obtained.




[0023] In the above-mentioned formula (IV), it is preferable that X is F or CF₃ from the viewpoint of stability of the compound and weather resistance, that d is an integer of 1 to 5 from the viewpoint of surface activating ability of the reactive emulsifying agent, that Y is COOM or SO₃M from the viewpoint of stability of the compound and that M is H or NH₄ from the viewpoint of water resistance of a coating film.

[0024] Examples of the compound represented by the above-mentioned formula (IV) are, for instance, CF₂=CF-O-CF₂CF(CF₃)-OCF₂CF₂-COOH, CF₂=CF-O-CF₂CF(CF₃)-OCF₂CF₂-COONH₄, CF₂=CF-O-CF₂CF(CF₃)-OCF₂CF₂SO₃H and CF₂=CF-O-CF₂CF(CF₃)-OCF₂CF₂SO₃NH₄.


[0025] From the viewpoint that an aqueous dispersion of a VdF copolymer having a small particle size can be obtained, CF₂=CF-O-CF₂CF(CF₃)-OCF₂CF₂-COOH and CF₂=CF-O-CF₂CF(CF₃)-OCF₂CF₂-SO₃H are preferable.

[0026] In the above-mentioned formula (V), it is preferable that e is an integer of 1 to 5 from the viewpoint of surface activating ability of the reactive emulsifying agent, that Y is COOM from the viewpoint of stability of the compound and that M is Na or NH₄ from the viewpoint of water resistance of a coating film.

[0027] Examples of the compound represented by the above-mentioned formula (V) are, for instance,






and




From the viewpoint that an aqueous dispersion of a VdF copolymer having a small particle size can be obtained, $\text{CH}_2=\text{CFCF}_2\text{OCF}(\text{CF}_3)\text{COONH}_4$ and $\text{CH}_2=\text{CFCF}_2\text{OCF}(\text{CF}_3)\text{CF}_2\text{OCF}(\text{CF}_3)\text{COONH}_4$ are preferable.

[0028] In the above-mentioned formula (VI), it is preferable that f is an integer of 1 to 5 from the viewpoint of surface activating ability of the reactive emulsifying agent, that Y is COOM from the viewpoint of stability of the compound and that M is H or NH_4 from the viewpoint of water resistance of a coating film.



[0029] Examples of the compound represented by the above-mentioned formula (VI) are, for instance,




and



[0030] From the viewpoint that an aqueous dispersion of a VdF copolymer having a small particle size can be obtained,



and



are preferable.

[0031] In the present invention, the above-mentioned VdF copolymer may be a copolymer comprising the above-mentioned VdF monomer and reactive emulsifying agent and in addition thereto, other fluorine-containing monomer. Examples of the other fluorine-containing monomer are, for instance, tetrafluoroethylene (TFE), trifluoroethylene (TrFE), chlorotrifluoroethylene (CTFE), hexafluoropropylene (HFP) and vinyl fluoride (VF).

[0032] From the viewpoint of copolymerizability of the VdF monomer, TFE, HFP and CTFE are preferable.

[0033] In the above-mentioned VdF copolymer, examples of combination of VdF, other fluorine-containing monomer and reactive emulsifying agent are, for instance, combinations of any of VdF/TFE, VdF/TFE/HFP, VdF/TFE/CTFE, VdF/TFE/TrFE, VdF/CTFE, VdF/HFP or VdF/TFE/HFP/CTFE with any of $\text{CF}_2=\text{CFCF}_2\text{COONH}_4$, $\text{CH}_2=\text{CFCF}_2\text{OCF}(\text{CF}_3)\text{COONH}_4$ or $\text{CH}_2=\text{CFCF}_2\text{OCF}(\text{CF}_3)\text{COONH}_4$. From the viewpoint of hardness of a coating film in case of the use for coating, the combination of VdF/TFE/CTFE with $\text{CH}_2=\text{CFCF}_2\text{OCF}(\text{CF}_3)\text{CF}_2\text{OCF}(\text{CF}_3)\text{COONH}_4$ is preferable.

[0034] A copolymerization ratio of VdF with the other fluorine-containing monomer in the above-mentioned VdF copolymer is from 60/40 to 95/5 % by weight, preferably 70/30 to 95/5 % by weight. When VdF is less than 60 % by weight, there is a tendency that compatibility of the VdF polymer with an acrylic polymer, which is a characteristic of the VdF polymer, is lowered. When more than 95 % by weight, since solubility of the seed particles to an acrylic ester and/or methacrylic acid ester is poor, there is a tendency that swelling of seed particles with the monomer does not advance rapidly at seed polymerization, a cast film prepared from the obtained emulsion has poor transparency and a gloss of the coating film from a paint cannot be obtained.

[0035] The above-mentioned reactive emulsifying agent may be contained in an amount of from 0.001 to 0.1 % by mole in the above-mentioned monomer combination.

[0036] An average particle size of the above-mentioned VdF copolymer is not more than 200 nm, preferably from 10 to 200 nm, more preferably from 50 to 150 nm. When the average particle size is less than 10 nm, there is a tendency that shape of the VdF copolymer is difficult to become spherical and film forming property is lowered. When more than 200 nm, storage stability, mechanical stability and chemical stability of the aqueous dispersion of the VdF copolymer tend to be lowered.

[0037] A solid content of the above-mentioned aqueous dispersion of the VdF copolymer is from 30 to 60 % (% by weight, hereinafter the same), preferably from 35 to 55 %, more preferably from 35 to 50 %. When the solid content is less than 30 %, there is a tendency that adjusting of viscosity is difficult when making a paint and that drying of the paint is slow. When more than 60 %, stability of the dispersion is lowered.

[0038] To the aqueous dispersion of the VdF copolymer of the present invention may be added a known fluorine-containing surfactant.

[0039] The known fluorine-containing surfactant is one or a mixture of compounds having surface activating ability and containing fluorine atom in the structure. For example, there are an acid represented by $\text{X}(\text{CF}_2)_n\text{COOH}$ (X is F or H, n is an integer of 6 to 20), its alkali metal salt, ammonium salt, amine salt or quaternary ammonium salt; an acid represented by $\text{Y}(\text{CH}_2\text{CF}_2)_m\text{COOH}$ (Y is F or Cl, m is an integer of 6 to 13), its alkali metal salt, ammonium salt, amine salt or quaternary ammonium salt; and the like. From weather resistance and water resistance points of view, ammonium salt of perfluorooctanoic acid and ammonium salt of perfluorononanoic acid are preferable.

[0040] The amount of the above-mentioned fluorine-containing surfactant is not more than 1.0 %, preferably not more than 0.5 %, more preferably not more than 0.2 % on the basis of water. When the amount of the fluorine-containing surfactant is more than 1.0 %, it is not preferable because there is a tendency that when forming a film by using an aqueous dispersion, the fluorine-containing surfactant precipitates in the film and water absorption increases to make the dispersion turbid in white.

[0041] The aqueous dispersion of the VdF copolymer of the present invention is one in which the VdF copolymer is dispersed in water. To the aqueous dispersion can be added a hydrophilic organic solvent.

[0042] To the aqueous dispersion of the VdF copolymer of the present invention can be added various additives to make an aqueous paint. By adding additives which are used generally for aqueous paints, for example, a pigment, thickener, dispersing agent, defoaming agent, anti-freezing agent, auxiliary for film formation and the like, the resulting aqueous dispersion can be used as paints for exterior of buildings and as paints for structures of construction.

[0043] The above-mentioned reactive emulsifying agent is a fluorine-containing compound having a polymerizable C=C double bond and a hydrophilic group in its molecule, and is at least one compound selected from the group consisting of those represented by the formula (I):




wherein a is an integer of 1 to 10, Y is SO_3M or COOM (M is H, NH_4 or an alkali metal), the formula (II):




wherein X is F or CF_3 , b is an integer of 1 to 5, Y is SO_3M or COOM (M is H, NH_4 or an alkali metal), the formula (III):




wherein X is F or CF_3 , c is an integer of 1 to 10, Y is SO_3M or COOM (M is H, NH_4 or an alkali metal), the formula (IV):



wherein X is F or CF_3 , d is an integer of 1 to 10, Y is SO_3M or COOM (M is H, NH_4 or an alkali metal), the formula (V):



wherein e is 0 or an integer of 1 to 10, Y is SO_3M or COOM (M is H, NH_4 or an alkali metal), and the formula (VI):




wherein f is an integer of 1 to 10, Y is SO_3M or COOM (M is H, NH_4 or an alkali metal).



[0044] In the above-mentioned formula (I), it is preferable that a is an integer of 1 to 5 from the viewpoint of surface activating ability of the reactive emulsifying agent, that Y is COOM from the viewpoint of stability of the compound and that M is H or NH_4 from the viewpoint of water resistance of a coating film.

[0045] Examples of the compound represented by the above-mentioned formula (I) are, for instance, $\text{CF}_2=\text{CF}-\text{CF}_2-\text{COONH}_4$, $\text{CF}_2=\text{CF}-\text{CF}_2-\text{COOH}$, $\text{CF}_2=\text{CF}-\text{CF}_2\text{CF}_2\text{COOH}$, $\text{CF}_2=\text{CF}-\text{CF}_2-\text{COONa}$, $\text{CF}_2=\text{CF}-\text{CF}_2-\text{SO}_3\text{NH}_4$, $\text{CF}_2=\text{CF}-\text{CF}_2-\text{SO}_3\text{H}$, $\text{CF}_2=\text{CF}-\text{CF}_2\text{CF}_2\text{SO}_3\text{H}$ and $\text{CF}_2=\text{CF}-\text{CF}_2\text{CF}_2\text{SO}_3\text{Na}$. $\text{CF}_2=\text{CFCF}_2\text{COONH}_4$ is preferable from the viewpoint that an aqueous dispersion of a VdF copolymer having a small particle size can be obtained at a high concentration.


[0046] In the above-mentioned formula (II), it is preferable that X is CF_3 from the viewpoint of stability of the compound, that b is an integer of 1 to 3 from the viewpoint of surface activating ability of the reactive emulsifying agent, that Y is COOM or SO_3M from the viewpoint of stability of the compound and that M is H or NH_4 from the viewpoint of water resistance of a coating film.

[0047] Examples of the compound represented by the above-mentioned formula (II) are, for instance,






and



From the viewpoint that an aqueous dispersion of a VdF copolymer having a small particle size can be obtained,



is preferable.

[0048] In the above-mentioned formula (III), it is preferable that X is F or CF₃ from the viewpoint of stability of the compound and weather resistance, that c is an integer of 1 to 5 from the viewpoint of surface activating ability of the reactive emulsifying agent, that Y is COOM or SO₃M from the viewpoint of stability of the compound and that M is H or NH₄ from the viewpoint of water resistance of a coating film.


[0049] Examples of the compound represented by the above-mentioned formula (III) are, for instance, CF₂=CF-OCF₂CF₂CF₂COOH, CF₂=CF-OCF₂CF₂COONH₄ and CF₂=CF-OCF₂COOH. CF₂=CF-OCF₂CF₂CF₂COOH is preferable from the viewpoint that an aqueous dispersion of a VdF copolymer having a small particle size can be obtained.



[0050] In the above-mentioned formula (IV), it is preferable that X is F or CF₃ from the viewpoint of stability of the compound and weather resistance, that d is an integer of 1 to 5 from the viewpoint of surface activating ability of the reactive emulsifying agent, that Y is COOM or SO₃M from the viewpoint of stability of the compound and that M is H or NH₄ from the viewpoint of water resistance of a coating film.

[0051] Examples of the compound represented by the above-mentioned formula (IV) are, for instance, CF₂=CF-O-CF₂CF(CF₃)-OCF₂CF₂-COOH, CF₂=CF-O-CF₂CF(CF₃)-OCF₂CF₂-COONH₄, CF₂=CF-O-CF₂CF(CF₃)-OCF₂CF₂SO₃H and CF₂=CF-O-CF₂CF(CF₃)-OCF₂CF₂SO₃NH₄. From the viewpoint that an aqueous dispersion of a VdF copolymer having a small particle size can be obtained, CF₂=CF-O-CF₂CF(CF₃)-OCF₂CF₂-COOH and CF₂=CF-O-CF₂CF(CF₃)-OCF₂CF₂-SO₃H are preferable.


[0052] In the above-mentioned formula (V), it is preferable that e is an integer of 1 to 5 from the viewpoint of surface activating ability of the reactive emulsifying agent, that Y is COOM from the viewpoint of stability of the compound and that M is Na or NH₄ from the viewpoint of water resistance of a coating film.

[0053] Examples of the compound represented by the above-mentioned formula (V) are, for instance,








and




From the viewpoint that an aqueous dispersion of a VdF copolymer having a small particle size can be obtained, $\text{CH}_2=\text{CFCF}_2\text{OCF}(\text{CF}_3)\text{COONH}_4$ and $\text{CH}_2=\text{CFCF}_2\text{OCF}(\text{CF}_3)\text{CF}_2\text{OCF}(\text{CF}_3)\text{COONH}_4$ are preferable.

[0054] In the above-mentioned formula (VI), it is preferable that f is an integer of 1 to 5 from the viewpoint of surface activating ability of the reactive emulsifying agent, that Y is COOM from the viewpoint of stability of the compound and that M is H or NH_4 from the viewpoint of water resistance of a coating film.



[0055] Examples of the compound represented by the above-mentioned formula (VI) are, for instance,




and



From the viewpoint that an aqueous dispersion of a VdF copolymer having a small particle size can be obtained,



and



are preferable.

[0056] When emulsion-polymerizing the above-mentioned VdF monomer and reactive emulsifying agent, it is possible to add a fluorine-containing monomer other than VdF, for example, tetrafluoroethylene (TFE), trifluoroethylene (TrFE), chlorotrifluoroethylene (CTFE), hexafluoropropylene (HFP) and vinyl fluoride (VF). From the viewpoint of copolymerizability of the VdF monomer, TFE, HFP and CTFE are preferable.

[0057] For the above-mentioned emulsion polymerization, it is possible to use a known fluorine-containing surfactant.

[0058] The known fluorine-containing surfactant is one or a mixture of compounds having surface activating ability and containing fluorine atom in the structure. For example, there are an acid represented by $\text{X}(\text{CF}_2)_n\text{COOH}$ (X is F or H, n is an integer of 6 to 20), its alkali metal salt, ammonium salt, amine salt or quaternary ammonium salt; an acid represented by $\text{Y}(\text{CH}_2\text{CF}_2)_m\text{COOH}$ (Y is F or Cl, m is an integer of 6 to 13), its alkali metal salt, ammonium salt, amine salt or quaternary ammonium salt; and the like. From weather resistance and water resistance points of view, ammonium salt of perfluorooctanoic acid and ammonium salt of perfluorononanoic acid are preferable.

[0059] An amount of the above-mentioned fluorine-containing surfactant is not more than 1.0 %, preferably not more than 0.5 %, more preferably not more than 0.2 % on the basis of water. When the amount of the fluorine-containing surfactant is more than 1.0 %, it is not preferable because there is a tendency that when forming a film by using an aqueous dispersion, the fluorine-containing surfactant precipitates in the film and water absorption increases to make the dispersion turbid in white.

[0060] In order to prepare the above-mentioned aqueous dispersion of the VdF copolymer, a reactor is charged with water as a polymerization solvent and the above-mentioned reactive emulsifying agent in an amount of 0.0001 to 10 %, preferably 0.0001 to 1.0 %, more preferably 0.001 to 0.5 % on the basis of the polymerization medium, and then pressure feeding of nitrogen gas and deaeration are repeated to remove dissolved air.

[0061] When the amount of the above-mentioned reactive emulsifying agent charged is less than 0.0001 %, there is a tendency that large particles having insufficient stability against sedimentation are obtained. When more than 10 %, there is a tendency that shape of the particles does not become spherical and film forming property when drying the aqueous dispersion is lowered.

[0062] Then the above-mentioned VdF monomer alone or a monomer mixture comprising the VdF monomer and the other fluorine-containing monomer is fed into the reactor under pressure to be a pressure of 1.0 to 50 kgf/cm².

[0063] In that case, a mixing ratio of the other fluorine-containing monomer may be from 0 to 30 % by mole.

[0064] Then as a polymerization initiator, for example, a persulfate such as ammonium persulfate, hydrogen peroxide, di-isopropyl peroxydicarbonate or azobisisobutyronitrile is introduced in an amount of 0.005 to 1.0 %, preferably 0.01 to 0.5 % on the basis of water. When the amount of the polymerization initiator is less than 0.005 %, polymerization speed tends to be extremely slow. When more than 1.0 %, electrolyte content tends to increase to make particle size large.

[0065] Further the above-mentioned VdF monomer or monomer mixture is fed continuously so that the pressure in the reactor becomes constant in the range of from 1.0 to 50 kgf/cm².

[0066] Polymerization is carried out for 5 to 100 hours under the conditions mentioned above.

[0067] After that, the inside conditions of the reactor are returned to normal temperature and normal pressure and then the polymerization is terminated to give an aqueous dispersion of the VdF copolymer.

[0068] An average particle size of the VdF copolymer of the aqueous dispersion obtained by the above-mentioned process can be controlled within not more than 200 nm. The average particle size can be controlled by the charging amount of the reactive emulsifying agent.

[0069] Also the solid content of the aqueous dispersion of the VdF copolymer which is prepared by the above-mentioned process can be controlled within 30 to 60 %. The solid content can be controlled by blowing the VdF monomer or the monomer mixture out from the reactor at the time when a given amount thereof has been fed continuously, and then stopping stirring to terminate the reaction.

[0070] Further the aqueous dispersion of the VdF seed polymer of the present invention is an aqueous dispersion of the VdF seed polymer which is obtained by emulsion-polymerizing an ethylenically unsaturated monomer in the presence of VdF copolymer particles. The VdF copolymer is a copolymer of VdF monomer and a reactive emulsifying agent.

[0071] The above-mentioned reactive emulsifying agent is a fluorine-containing compound having a polymerizable C=C double bond and a hydrophilic group in its molecule, and is at least one compound selected from the group consisting of those represented by the formula (I):




wherein a is an integer of 1 to 10, Y is SO₃M or COOM (M is H, NH₄ or an alkali metal), the formula (II):




wherein X is F or CF₃, b is an integer of 1 to 5, Y is SO₃M or COOM (M is H, NH₄ or an alkali metal), the formula (III):




wherein X is F or CF₃, c is an integer of 1 to 10, Y is SO₃M or COOM (M is H, NH₄ or an alkali metal), the formula (IV):



wherein X is F or CF₃, d is an integer of 1 to 10, Y is SO₃M or COOM (M is H, NH₄ or an alkali metal), the formula (V):



wherein e is 0 or an integer of 1 to 10, Y is SO₃M or COOM (M is H, NH₄ or an alkali metal), and the formula (VI):






wherein f is an integer of 1 to 10, Y is SO₃M or COOM (M is H, NH₄ or an alkali metal).

[0072] In the above-mentioned formula (I), it is preferable that a is an integer of 1 to 5 from the viewpoint of surface activating ability of the reactive emulsifying agent, that Y is COOM from the viewpoint of stability of the compound and that M is H or NH₄ from the viewpoint of water resistance of a coating film.


[0073] Examples of the compound represented by the above-mentioned formula (I) are, for instance, CF₂=CF-CF₂-COONH₄, CF₂=CF-CF₂-COOH, CF₂=CF-CF₂CF₂COOH, CF₂=CF-CF₂-COONa, CF₂=CF-CF₂-SO₃NH₄, CF₂=CF-CF₂-SO₃H, CF₂=CF-CF₂CF₂SO₃H and CF₂=CF-CF₂CF₂SO₃Na. CF₂=CF-CF₂COONH₄ is preferable from the viewpoint that an aqueous dispersion of a VdF copolymer having a small particle size can be obtained at a high concentration.

[0074] In the above-mentioned formula (II), it is preferable that X is CF₃ from the viewpoint of stability of the compound, that b is an integer of 1 to 3 from the viewpoint of surface activating ability of the reactive emulsifying agent, that Y is COOM or SO₃M from the viewpoint of stability of the compound and that M is H or NH₄ from the viewpoint of water resistance of a coating film.

[0075] Examples of the compound represented by the above-mentioned formula (II) are, for instance,



and



From the viewpoint that an aqueous dispersion of a VdF copolymer having a small particle size can be obtained,



is preferable.

[0076] In the above-mentioned formula (III), it is preferable that X is F or CF₃ from the viewpoint of stability of the compound and weather resistance, that c is an integer of 1 to 5 from the viewpoint of surface activating ability of the reactive emulsifying agent, that Y is COOM or SO₃M from the viewpoint of stability of the compound and that M is H or NH₄ from the viewpoint of water resistance of a coating film.

[0077] Examples of the compound represented by the above-mentioned formula (III) are, for instance, CF₂=CF-OCF₂CF₂CF₂COOH, CF₂=CF-OCF₂CF₂COONH₄ and CF₂=CF-OCF₂COOH. CF₂=CF-OCF₂CF₂CF₂COOH is preferable from the viewpoint that an aqueous dispersion of a VdF copolymer having a small particle size can be obtained.




[0078] In the above-mentioned formula (IV), it is preferable that X is F or CF₃ from the viewpoint of stability of the compound and weather resistance, that d is an integer of 1 to 5 from the viewpoint of surface activating ability of the

reactive emulsifying agent, that Y is COOM or SO₃M from the viewpoint of stability of the compound and that M is H or NH₄ from the viewpoint of water resistance of a coating film.


[0079] Examples of the compound represented by the above-mentioned formula (IV) are, for instance, CF₂=CF-O-CF₂CF(CF₃)-OCF₂CF₂-COOH, CF₂=CF-O-CF₂CF(CF₃)-OCF₂CF₂-COONH₄, CF₂=CF-O-CF₂CF(CF₃)-OCF₂CF₂SO₃H and CF₂=CF-O-CF₂CF(CF₃)-OCF₂CF₂SO₃NH₄. From the viewpoint that an aqueous dispersion of a VdF copolymer having a small particle size can be obtained, CF₂=CF-O-CF₂CF(CF₃)-OCF₂CF₂-COOH and CF₂=CF-O-CF₂CF(CF₃)-OCF₂CF₂-SO₃H are preferable.

[0080] In the above-mentioned formula (V), it is preferable that e is an integer of 1 to 5 from the viewpoint of surface activating ability of the reactive emulsifying agent, that Y is COOM from the viewpoint of stability of the compound and that M is Na or NH₄ from the viewpoint of water resistance of a coating film.

[0081] Examples of the compound represented by the above-mentioned formula (V) are, for instance,





and




From the viewpoint that an aqueous dispersion of a VdF copolymer having a small particle size can be obtained, CH₂=CFCF₂OCF(CF₃)COONH₄ and CH₂=CFCF₂OCF(CF₃)CF₂OCF(CF₃)COONH₄ are preferable.


[0082] In the above-mentioned formula (VI), it is preferable that f is an integer of 1 to 5 from the viewpoint of surface activating ability of the reactive emulsifying agent, that Y is COOM from the viewpoint of stability of the compound and that M is H or NH₄ from the viewpoint of water resistance of a coating film.

[0083] Examples of the compound represented by the above-mentioned formula (VI) are, for instance,








and



From the viewpoint that an aqueous dispersion of a VdF copolymer having a small particle size can be obtained,



and



are preferable.

[0084] The VdF seed polymer in the present invention is a seed polymer of an ethylenically unsaturated monomer, which is prepared by using, as seeds, the above-mentioned VdF copolymer particles. As the ethylenically unsaturated monomer, there are, for example, a monomer having functional group and a vinyl compound. Examples of the monomer having functional group are, for instance, an unsaturated carboxylic acid such as acrylic acid, methacrylic acid, maleic acid or crotonic acid; an acrylic ester such as methyl acrylate; a methacrylic acid ester such as methyl methacrylate (MMA); an amide compound such as acrylamide, methacrylamide, N-methylacrylamide, N-methylolacrylamide, N-butoxymethylacrylamide, N-methylolmethacrylamide, N-methylmethacrylamide or N-butoxymethylmethacrylamide; a hydroxyl-containing monomer such as hydroxyethyl acrylate, hydroxyethyl methacrylate, hydroxypropyl acrylate or hydroxypropyl methacrylate; an epoxy-containing monomer such as glycidyl acrylate or glycidyl methacrylate; a silanol-containing monomer such as γ -trimethoxysilane methacrylate, or γ -triethoxysilane methacrylate; and an aldehyde-containing monomer such as acrolein. Examples of the vinyl compound are, for instance, styrene (St) and acrylonitrile. From the viewpoint of compatibility with the VdF copolymer, an acrylic ester and/or a methacrylic acid ester are preferable.

[0085] The VdF copolymer as the seed in the above-mentioned VdF seed polymer may be a copolymer comprising the above-mentioned VdF, reactive emulsifying agent and other fluorine-containing monomer. Examples of the other fluorine-containing monomer are, for instance, tetrafluoroethylene (TFE), trifluoroethylene (TrFE), chlorotrifluoroethylene (CTFE), hexafluoropropylene (HFP) and vinyl fluoride (VF). From the viewpoint of copolymerizability of the VdF monomer, TFE, HFP and CTFE are preferable.

[0086] In the above-mentioned VdF copolymer, examples of combination of VdF, other fluorine-containing monomer

and reactive emulsifying agent are, for instance, combinations of any of VdF/TFE, VdF/TFE/HFP, VdF/TFE/CTFE, VdF/TFE/TrFE, VdF/CTFE, VdF/HFP or VdF/TFE/HFP/CTFE with any of $\text{CF}_2=\text{CFCF}_2\text{COONH}_4$, $\text{CH}_2=\text{CFCF}_2\text{OCF}(\text{CF}_3)\text{COONH}_4$ or $\text{CH}_2=\text{CFCF}_2\text{OCF}(\text{CF}_3)\text{COONH}_4$.

[0087] From the viewpoint of compatibility with an acrylic resin, the combination of VdF/TFE/CTFE with $\text{CH}_2=\text{CFCF}_2\text{OCF}(\text{CF}_3)\text{CF}_2\text{OCF}(\text{CF}_3)\text{COONH}_4$ is preferable.

[0088] A copolymerization ratio of VdF with the other fluorine-containing monomer in the above-mentioned VdF copolymer is from 60/40 to 95/5 %, preferably 70/30 to 95/5 %. When VdF is less than 60 %, there is a tendency that compatibility of the VdF polymer with an acrylic polymer, which is a characteristic of the VdF polymer, is lowered. When more than 95 %, since solubility of the seed particles to an acrylic ester and/or methacrylic acid ester is poor, there is a tendency that swelling of seed particles with the monomer does not advance rapidly at seed polymerization, a cast film prepared from the obtained emulsion has poor transparency and a gloss of the coating film from a paint cannot be obtained.

[0089] The above-mentioned reactive emulsifying agent may be contained in an amount of from 0.001 to 0.1 % by mole in the above-mentioned monomer combination.

[0090] The above-mentioned VdF seed polymer is one prepared by polymerizing 20 to 100 parts by weight of the ethylenically unsaturated monomer in the presence of 100 parts by weight of the VdF copolymer as the seed.

[0091] An average particle size of the above-mentioned VdF seed polymer is not more than 250 nm, preferably from 50 to 250 nm, more preferably from 100 to 160 nm. When the average particle size is less than 50 nm, there is a tendency that a viscosity of the aqueous dispersion increases and the aqueous dispersion having a high concentration cannot be obtained. When more than 250 nm, sedimentation and coagulation of particles occur during the storage of the aqueous dispersion and further when forming a film, gloss tends not to be obtained.

[0092] A content of the VdF seed polymer of the above-mentioned dispersion of the VdF seed polymer is from 30 to 60 %, by weight preferably from 35 to 55 %, more preferably from 35 to 50 %. When the content is less than 30 %, there is a tendency that adjusting of viscosity is difficult when making a paint and that drying of the paint is slow. When more than 60 %, stability of the dispersion is lowered.

[0093] To the aqueous dispersion of the VdF seed polymer of the present invention may be added a known fluorine-containing surfactant.

[0094] The known fluorine-containing surfactant is one or a mixture of compounds having surface activating ability and containing fluorine atom in the structure. For example, there are an acid represented by $\text{X}(\text{CF}_2)_n\text{COOH}$ (X is F or H, n is an integer of 6 to 20), its alkali metal salt, ammonium salt, amine salt or quaternary ammonium salt; an acid represented by $\text{Y}(\text{CH}_2\text{CF}_2)_m\text{COOH}$ (Y is F or Cl, m is an integer of 6 to 13), its alkali metal salt, ammonium salt, amine salt or quaternary ammonium salt; and the like. From weather resistance and water resistance points of view, ammonium salt of perfluorooctanoic acid and ammonium salt of perfluorononanoic acid are preferable.

[0095] An amount of the above-mentioned fluorine-containing surfactant is not more than 1.0 %, preferably not more than 0.5 %, more preferably not more than 0.2 % on the basis of water. When the amount of the fluorine-containing surfactant is more than 1.0 %, it is not preferable because there is a tendency that when forming a film by using an aqueous dispersion, the fluorine-containing surfactant precipitates in the film and water absorption increases to make the dispersion turbid in white.

[0096] The aqueous dispersion of the VdF seed polymer of the present invention is one in which the VdF seed copolymer is dispersed in water. To the aqueous dispersion can be added a hydrophilic organic solvent.

[0097] To the aqueous dispersion of the VdF seed polymer of the present invention can be added various additives to make an aqueous paint. By adding additives which are used generally for aqueous paints, for example, a pigment, thickener, dispersing agent, defoaming agent, anti-freezing agent, auxiliary for film formation and the like, the resulting aqueous dispersion can be used as paints for exterior of buildings and as paints for structures of construction.

[0098] In order to obtain the above-mentioned VdF copolymer, VdF monomer may be emulsion-polymerized with a reactive emulsifying agent. The reactive emulsifying agent is a fluorine-containing compound having a copolymerizable $\text{C}=\text{C}$ double bond and a hydrophilic group in its molecule and is at least one compound selected from the group consisting of those represented by the above-mentioned formula (I):



wherein a is an integer of 1 to 10, Y is SO_3M or COOM (M is H, NH_4 or an alkali metal), the formula (II):




wherein X is F or CF_3 , b is an integer of 1 to 5, Y is SO_3M or COOM (M is H, NH_4 or an alkali metal), the formula (III):




wherein X is F or CF_3 , c is an integer of 1 to 10, Y is SO_3M or COOM (M is H, NH_4 or an alkali metal), the formula (IV):



wherein X is F or CF_3 , d is an integer of 1 to 10, Y is SO_3M or COOM (M is H, NH_4 or an alkali metal), the formula (V):



wherein e is 0 or an integer of 1 to 10, Y is SO_3M or COOM (M is H, NH_4 or an alkali metal), and the formula (VI):




wherein f is an integer of 1 to 10, Y is SO_3M or COOM (M is H, NH_4 or an alkali metal).



[0099] In the above-mentioned formula (I), it is preferable that a is an integer of 1 to 5 from the viewpoint of surface activating ability of the reactive emulsifying agent, that Y is COOM from the viewpoint of stability of the compound and that M is H or NH_4 from the viewpoint of water resistance of a coating film.

[0100] Examples of the compound represented by the above-mentioned formula (I) are, for instance, $\text{CF}_2=\text{CF}-\text{CF}_2-\text{COONH}_4$, $\text{CF}_2=\text{CF}-\text{CF}_2-\text{COOH}$, $\text{CF}_2=\text{CF}-\text{CF}_2\text{CF}_2\text{COOH}$, $\text{CF}_2=\text{CF}-\text{CF}_2-\text{COONa}$, $\text{CF}_2=\text{CF}-\text{CF}_2-\text{SO}_3\text{NH}_4$, $\text{CF}_2=\text{CF}-\text{CF}_2-\text{SO}_3\text{H}$, $\text{CF}_2=\text{CF}-\text{CF}_2\text{CF}_2\text{SO}_3\text{H}$ and $\text{CF}_2=\text{CF}-\text{CF}_2\text{CF}_2\text{SO}_3\text{Na}$. $\text{CF}_2=\text{CFCF}_2\text{COONH}_4$ is preferable from the viewpoint that an aqueous dispersion of a VdF copolymer having a small particle size can be obtained at a high concentration.


[0101] In the above-mentioned formula (II), it is preferable that X is CF_3 from the viewpoint of stability of the compound, that b is an integer of 1 to 3 from the viewpoint of surface activating ability of the reactive emulsifying agent, that Y is COOM or SO_3M from the viewpoint of stability of the compound and that M is H or NH_4 from the viewpoint of water resistance of a coating film.

[0102] Examples of the compound represented by the above-mentioned formula (II) are, for instance,





and



From the viewpoint that an aqueous dispersion of a VdF copolymer having a small particle size can be obtained,



is preferable.

[0103] In the above-mentioned formula (III), it is preferable that X is F or CF₃ from the viewpoint of stability of the compound and weather resistance, that c is an integer of 1 to 5 from the viewpoint of surface activating ability of the reactive emulsifying agent, that Y is COOM or SO₃M from the viewpoint of stability of the compound and that M is H or NH₄ from the viewpoint of water resistance of a coating film.


[0104] Examples of the compound represented by the above-mentioned formula (III) are, for instance, CF₂=CF-OCF₂CF₂CF₂COOH, CF₂=CF-OCF₂CF₂COONH₄ and CF₂=CF-OCF₂COOH. CF₂=CF-OCF₂CF₂CF₂COOH is preferable from the viewpoint that an aqueous dispersion of a VdF copolymer having a small particle size can be obtained.



[0105] In the above-mentioned formula (IV), it is preferable that X is F or CF₃ from the viewpoint of stability of the compound and weather resistance, that d is an integer of 1 to 5 from the viewpoint of surface activating ability of the reactive emulsifying agent, that Y is COOM or SO₃M from the viewpoint of stability of the compound and that M is H or NH₄ from the viewpoint of water resistance of a coating film.

[0106] Examples of the compound represented by the above-mentioned formula (IV) are, for instance, CF₂=CF-O-CF₂CF(CF₃)-OCF₂CF₂-COOH, CF₂=CF-O-CF₂CF(CF₃)-OCF₂CF₂-COONH₄, CF₂=CF-O-CF₂CF(CF₃)-OCF₂CF₂SO₃H and CF₂=CF-O-CF₂CF(CF₃)-OCF₂CF₂SO₃NH₄. From a point that an aqueous dispersion of a VdF copolymer having a small particle size can be obtained, CF₂=CF-O-CF₂CF(CF₃)-OCF₂CF₂-COOH and CF₂=CF-O-CF₂CF(CF₃)-OCF₂CF₂-SO₃H are preferable.


[0107] In the above-mentioned formula (V), it is preferable that e is an integer of 1 to 5 from the viewpoint of surface activating ability of the reactive emulsifying agent, that Y is COOM from the viewpoint of stability of the compound and that M is Na or NH₄ from the viewpoint of water resistance of a coating film.

[0108] Examples of the compound represented by the above-mentioned formula (V) are, for instance,








and




From the viewpoint that an aqueous dispersion of a VdF copolymer having a small particle size can be obtained, $\text{CH}_2=\text{CFCF}_2\text{OCF}(\text{CF}_3)\text{COONH}_4$ and $\text{CH}_2=\text{CFCF}_2\text{OCF}(\text{CF}_3)\text{CF}_2\text{OCF}(\text{CF}_3)\text{COONH}_4$ are preferable.

[0109] In the above-mentioned formula (VI), it is preferable that f is an integer of 1 to 5 from the viewpoint of surface activating ability of the reactive emulsifying agent, that Y is COOM from the viewpoint of stability of the compound and that M is H or NH_4 from the viewpoint of water resistance of a coating film.



[0110] Examples of the compound represented by the above-mentioned formula (VI) are, for instance,




and



From the viewpoint that an aqueous dispersion of a VdF copolymer having a small particle size can be obtained,



and



are preferable.

[0111] In emulsion-polymerizing the above-mentioned VdF monomer with the above-mentioned reactive emulsifying agent, a fluorine-containing monomer other than VdF can be used. Examples of the other fluorine-containing monomer, are, for instance, tetrafluoroethylene (TFE), trifluoroethylene (TrFE), chlorotrifluoroethylene (CTFE), hexafluoropropylene (HFP) and vinyl fluoride (VF). From the viewpoint of copolymerizability of the VdF monomer, TFE, HFP and CTFE are preferable.

[0112] In the above-mentioned emulsion polymerization, a known fluorine-containing surfactant can be used.

[0113] The known fluorine-containing surfactant is one or a mixture of compounds having surface activating ability and containing fluorine atom in the structure. For example, there are an acid represented by $\text{X}(\text{CF}_2)_n\text{COOH}$ (X is F or H, n is an integer of 6 to 20), its alkali metal salt, ammonium salt, amine salt or quaternary ammonium salt; and an acid represented by $\text{Y}(\text{CH}_2\text{CF}_2)_m\text{COOH}$ (Y is F or Cl, m is an integer of 6 to 13), its alkali metal salt, ammonium salt, amine salt or quaternary ammonium salt. From weather resistance and water resistance points of view, ammonium salt of perfluorooctanoic acid and ammonium salt of perfluorononanoic acid are preferable.

[0114] An amount of the above-mentioned fluorine-containing surfactant is not more than 1.0 %, preferably not more than 0.5 %, more preferably not more than 0.2 % on the basis of water. When the amount of the fluorine-containing surfactant is more than 1.0 %, it is not preferable because there is a tendency that when forming a film by using an aqueous dispersion, the fluorine-containing surfactant precipitates in the film and water absorption increases to make the dispersion turbid in white.

[0115] In order to prepare the above-mentioned aqueous dispersion of the VdF seed polymer, a reactor is charged with water as a polymerization solvent and the above-mentioned reactive emulsifying agent in an amount of 0.00001 to 10 %, preferably 0.0001 to 1.0 %, more preferably 0.001 to 0.5 % on the basis of the polymerization solvent, and then pressure feeding of nitrogen gas and deaeration are repeated to remove dissolved air.

[0116] When the amount of the above-mentioned reactive emulsifying agent charged is less than 0.00001 %, there is a tendency that large particles having insufficient stability against sedimentation are obtained. When more than 10 %, there is a tendency that shape of the particles does not become spherical and film forming property when drying the aqueous dispersion is lowered.

[0117] Then the above-mentioned VdF monomer alone or a monomer mixture comprising the VdF monomer and the other fluorine-containing monomer is fed into the reactor under pressure to be a pressure of 1.0 to 50 kgf/cm².

[0118] In that case, a mixing ratio of the other fluorine-containing monomer may be from 0 to 30 % by mole.

[0119] Then as a polymerization initiator, for example, a persulfate such as ammonium persulfate, hydrogen peroxide, di-isopropyl peroxydicarbonate or azobisisobutyronitrile is introduced in an amount of 0.0001 to 0.5 %, preferably 0.001 to 0.1 % on the basis of water. When the amount of the polymerization initiator is less than 0.0001 %, polymerization speed which can be used practically tends not to be obtainable. When more than 0.5 %, controlling of reaction heat tends to become difficult.

[0120] Further the above-mentioned VdF monomer or monomer mixture is supplied continuously so that the pressure in the reactor becomes constant in the range of 1 to 50 kgf/cm² (98 - 4900 kPa), preferably 5 to 40 kgf/cm² (490 - 3920 kPa). When the pressure is less than 1 kgf/cm² (98 kPa), practical polymerization speed tends not to be obtainable. When more than 50 kgf/cm² (4900 kPa), controlling of reaction heat tends to become difficult.

[0121] Polymerization is carried out for 5 to 100 hours under the conditions mentioned above.

[0122] After that, the inside conditions of the reactor are returned to normal temperature and normal pressure and then the polymerization is terminated to give an aqueous dispersion of the VdF copolymer.

[0123] Then to the above-mentioned aqueous dispersion of the VdF copolymer is added 20 to 100 parts by weight, preferably 30 to 100 parts by weight, more preferably 40 to 100 parts by weight of the above-mentioned ethylenically unsaturated monomer on the basis of 100 parts by weight of the VdF copolymer.

[0124] When an amount of the above-mentioned ethylenically unsaturated monomer is less than 20 parts by weight, transparency and gloss of a coating film tend to be lowered.

[0125] Further immediately after that, as a polymerization initiator, for example, a persulfate such as ammonium persulfate is added in an amount of 0.05 to 2.0 parts by weight on the basis of 100 parts by weight of the above-mentioned ethylenically unsaturated monomer and polymerization is initiated. The polymerization is carried out at a temperature of 20° to 90°C for 0.5 to 6 hours, followed by adjusting pH with an alkaline solution and then filtrating with a metal net to obtain an aqueous dispersion of the VdF seed polymer.

[0126] An average particle size of the VdF seed polymer of the aqueous dispersion obtained by the above-mentioned process can be controlled within not more than 250 nm. The average particle size can be controlled by the amount of the reactive emulsifying agent.

[0127] Also the content of the VdF seed polymer in the aqueous dispersion of the VdF seed polymer which is prepared by the above-mentioned process can be controlled within 30 to 60 % by weight. The content can be controlled by blowing the VdF monomer or the monomer mixture out from the reactor at the time when a given amount thereof has been fed continuously, and then stopping stirring to terminate the reaction.

[0128] The present invention is then explained by referring to Examples, but is not limited thereto.

[0129] The numbers and structural formulae of the reactive emulsifying agents used in Examples and Comparative Examples are shown in Table 1.

Table 1

No. of reactive emulsifying agent	structural formula of reactive emulsifying agent
1	$\text{CF}_2=\text{CFCF}_2\text{-COOH}$
2	$\text{CF}_2=\text{CF-O-CF}_2\text{CF}_2\text{CF}_2\text{-COOH}$
3	$\text{CF}_2=\text{CF-O-CF}_2\text{CF}(\text{CF}_3)\text{-OCF}_2\text{CF}_2\text{-COOH}$
4	$\text{CF}_2=\text{CF-O-CF}_2\text{CF}(\text{CF}_3)\text{-OCF}_2\text{CF}_2\text{-SO}_3\text{H}$
5	$\text{CH}_2=\text{CFCF}_2\text{-O-CF}(\text{CF}_3)\text{CF}_2\text{-O-CF}(\text{CF}_3)\text{-COOH}$
6	$\text{CH}_2=\text{CFCF}_2\text{-O-CF}(\text{CF}_3)\text{-COOH}$
7	$\text{CF}_2=\text{CFCF}_2\text{-O-CF}(\text{CF}_3)\text{CF}_2\text{-O-CF}(\text{CF}_3)\text{-COOH}$

Example 1

[0130] A one-liter pressure resistive reactor equipped with a stirrer was charged with 500 ml of deionized water and 5.0 g of a reactive emulsifying agent (No. 1) shown in Table 1 and then introduction of a pressurized nitrogen gas and deaeration were repeated to remove the dissolved air. A monomer mixture of VdF (80 % by mole) and TFE (20 % by mole) was pressure-fed until the inside pressure of the reactor became 10 kgf/cm² at 60°C. Then 0.2 g of ammonium persulfate was added, the monomer mixture was continuously supplied to maintain the inside pressure of the reactor constant at 10 kgf/cm², and the reaction was carried out for 20 hours. Afterwards the inside conditions of the reactor were returned to normal temperature and normal pressure to terminate the polymerization and give an aqueous dispersion of a VdF polymer of the present invention, and the following tests were carried out.

The tests were carried out in the following manner.

Solid content:

The aqueous dispersion was dried at 150°C for one hour in a vacuum dryer. The ratio of a weight after drying to a weight before drying of the aqueous dispersion is shown by percentage.

Average particle size:

Measured by a laser beam scattering particle size measuring device (tradename ELS-3000 available from Otsuka Denshi Kabushiki Kaisha).

Particle size distribution:

Particle size was measured with a laser beam scattering particle size measuring device (tradename ELS-3000 available from Otsuka Denshi Kabushiki Kaisha), and a ratio of a weight average particle size \bar{d}_w to a number average particle size \bar{d}_n (\bar{d}_w/\bar{d}_n) was assumed to be particle size distribution.

Stability against sedimentation:

The aqueous dispersion was allowed to stand at 25°C for 60 days and then evaluated as follows:

The aqueous dispersion when checked with naked eyes was evaluated to be "O" where there was no change in dispersed state, to be "Δ" when sedimentation of particles and phase separation occurred but re-dispersing procedure was possible by shaking, and to be "X" when sedimentation of particles and phase separation occurred and re-dispersing procedure could not be done even by shaking.

[0131] The results are shown in Table 2.

Examples 2 to 13

[0132] The aqueous dispersion of the VdF copolymer of the present invention was obtained in the same manner as in Example 1 except that the polymerization conditions shown in Table 2 were employed. The same tests as in Example 1 were carried out. The results are shown in Table 2.

Comparative Examples 1 to 6

[0133] An aqueous dispersion of a VdF copolymer or an aqueous dispersion of a tetrafluoroethylene-propylene copolymer was obtained in the same manner as in Example 1 except that the polymerization conditions shown in Table 2 were employed. The same tests as in Example 1 were carried out. The results are shown in Table 2.

Table 2

Polymerization conditions										
Monomers supplied (% by mole)										
	Ex.1	Ex.2	Ex.3	Ex.4	Ex.5	Ex.6	Ex.7	Ex.8	Ex.9	Ex.10
VdF ¹⁾	80	80	80	80	100	80	75	72	75	75
TFE ¹⁾	20	20	20	20	-	20	15	20	15	15
CTFE ¹⁾	-	-	-	-	-	-	10	-	10	10
HFP ¹⁾	-	-	-	-	-	-	-	8	-	-
P ¹⁾	-	-	-	-	-	-	-	-	-	-
No. of reactive emulsifying agent	1	2	3	4	5	5	5	5	5	5
Added amount based on water (% by weight)	1.0	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.5	0.01
Added amount of ammonium salt of perfluorooctanoic acid based on water (% by weight)										
	-	-	-	-	-	-	-	-	-	-
Polymerization pressure (kgf/cm ² G)	10	10	10	10	20	10	8	8	8	8
Polymerization time (hr)	20	27	25	23	36	24	25	21	30	50
Tests										
Solid content (% by weight)	31.0	30.5	31.2	30.3	30.2	30.6	37.4	34.3	39.9	35.0
Average particle size (nm)	178.1	162.3	173.1	154.7	131.4	120.0	116.2	105.8	100.4	156.4
Particle size distribution (dw/dn)	1.27	1.54	1.48	1.55	1.38	1.38	1.56	1.43	1.45	1.59
Stability against sedimentation	○	○	○	○	○	○	○	○	○	○

- continued -

- continued -

Polymerization conditions									
Monomers supplied (% by mole)									
	Ex. 11	Ex. 12	Ex. 13	Com. Ex. 1	Com. Ex. 2	Com. Ex. 3	Com. Ex. 4	Com. Ex. 5	Com. Ex. 6
VdF ¹⁾	80	75	75	80	75	72	75	40	-
TFE ¹⁾	20	15	15	20	15	20	15	60	50
CTFE ¹⁾	-	10	10	-	10	-	10	-	-
HFP ¹⁾	-	-	-	-	-	8	-	-	-
P ¹⁾	-	-	-	-	-	-	-	-	50
No. of reactive emulsifying agent									
Added amount based on water									
(% by weight)									
	7	6	5	-	-	-	-	5	5
	0.1	0.5	0.5	-	-	-	-	1.0	1.0
Added amount of ammonium salt of perfluorooctanoic acid based on water (% by weight)									
	-	-	0.1	1.0	0.5	0.1	2.0	-	-
Polymerization pressure (kgf/cm ² G)									
	10	8	8	10	8	8	8	8	10
Polymerization time (hr)									
	26	25	26	20	23	21	16	13	68
Tests									
Solid content (% by weight)	31.6	32.0	41.9	24.6	34.6	32.0	38.8	21.1	30.1
Average particle size (nm)	131.3	49.2	104.3	269.2	221.6	234.5	68.5	216.0	231.6
Particle size distribution (dw/dn)	1.27	1.39	1.02	1.08	1.05	1.03	1.12	2.04	1.51
Stability against sedimentation	○	○	○	×	×	×	△	×	△
1) VdF: Vinylidene fluoride, TFE: Tetrafluoroethylene, CTFE: Chlorotrifluoroethylene,									
HFP: Hexafluoropropylene, P: Propylene									

Example 14

[0134] A 200 ml four-necked flask equipped with a stirrer, cooling tube and thermometer was charged with 70 g of the aqueous dispersion of the VdF copolymer prepared in Example 7, and thereto was added an alkali salt of alkylallylsulfosuccinate (available from Sanyo Kasei Kogyo Kabushiki Kaisha, tradename: ELEMNOL JS2) in an amount of 0.5 % on the basis of the solid resin as a polymerizable emulsifying agent for securing stability of seed particles in seed polymerization, followed by heating in a water bath with stirring. When the inside temperature of the flask reached 80°C, to the reactor was added dropwise for an hour an emulsion prepared by emulsifying, with the 0.5 % aqueous solution of an alkali salt of alkylallylsulfosuccinate, a monomer mixture of 11.2 g of methyl methacrylate (hereinafter referred to as MMA) and 1.5 g of polyoxyethylene methacrylate (available from Nippon Yushi Kabushiki Kaisha, tradename: PME 400, number of moles of ethylene oxide: 9). Immediately after completion of the addition, 1 ml of a 2 % aqueous solution of ammonium persulfate was added to initiate the reaction. Three hours after the initiation of the reaction, the inside temperature of the flask was raised to 85°C, and after keeping at that temperature for one hour, then cooled. Then pH was adjusted to 7 with aqueous ammonia, followed by filtration with 300 mesh metal net to give an aqueous dispersion of a VdF seed polymer of the present invention with bluish white color. Then the following tests were carried out.

[0135] The tests were carried out in the following manner.

(1) With respect to an aqueous dispersion of a VdF seed polymer

[0136]

Solid content, Average particle size: Tests were carried out in the same manner as in Example 1.

Viscosity: Measurement was made at 25°C with a B type viscometer.

Minimum film forming temperature (MFT): Minimum temperature at which a continuous film was formed was measured with a thermal gradient tester (available from Rigaku Kogyo Kabushiki Kaisha).

(2) With respect to a film formed by using the above-mentioned aqueous dispersion of the VdF seed polymer

[0137] Transparency: An aqueous dispersion was poured in a 10 cm diameter petri dish so that a dried film thickness became 200 µm, and then dried at 80°C for 24 hours. With respect to the obtained film, transmittance of light having a wavelength of 800 nm was measured and evaluated as follows.

[0138] When the film was transparent (when transmittance was not less than 90 %), the transparency was evaluated as O. When semitransparent (when transmittance was from 60 to 90 %), the transparency was evaluated as Δ. When turbid in white (when transmittance was not more than 60 %), the transparency was evaluated as X.

[0139] Water resistance: The film was cut to 2 cm × 4 cm and then dipped in hot water of 50°C for one week. A ratio of increase in weight, which was calculated by the following equation, was assumed to be a water absorption ratio.

$$\text{Water absorption ratio (\%)} = \frac{(\text{Weight after dipped} - \text{Initial weight})}{\text{Initial weight}} \times 100$$

[0140] A ratio of decrease in weight, which was calculated by the following equation after re-drying, was assumed to be an elution ratio.

$$\text{Elution ratio (\%)} = \frac{(\text{Initial weight} - \text{Weight after re-dried})}{\text{Initial weight}} \times 100$$

(3) With respect to a coating obtained from the above-mentioned aqueous dispersion of the VdF seed polymer

[0141] On the basis of 100 parts by weight of a solid resin contained in the aqueous dispersion obtained in Example 14 were added 50 parts by weight of titanium oxide (available from Ishihara Sangyo Kabushiki Kaisha, tradename: CR90) as a filler, 2 parts by weight of DISCOAT H-14 (available from Nippon Nyukazai Kabushiki Kaisha) as a dispersing agent, 1 part by weight of ethylene glycol as an antifreezing agent, 0.5 part by weight of FS ANTIFOAM 013B (available from Nippon Nyukazai Kabushiki Kaisha) as a defoaming agent, 0.5 part by weight of SN THICKENER A-818 (available

from Sunnopco Kabushiki Kaisha) as a thickener and 10 parts by weight of TEXANOL CS12 (available from Chisso Kabushiki Kaisha) as an auxiliary for film formation, followed by mixing sufficiently with a dispersing stirrer to give a paint. Then the following tests were carried out.

[0142] Gloss: The obtained paint was applied on a glass plate by means of an applicator so that the coating thickness after drying was 20 μm . After drying at room temperature for one week, gloss of the coating was measured with a gloss meter (available from Suga Shikenki Kabushiki Kaisha) with an angle of reflection of 60°.

[0143] Weather resistance: The obtained paint was applied by means of an airless spray gun on a slate which had been coated with an aqueous epoxy resin sealer EM-0150 (available from Sanyo Kasei Kogyo Kabushiki Kaisha) so that the coating thickness after drying was 100 μm . The coated slates were dried at room temperature for 24 hours and further at 80°C for two hours. After those coated slates were allowed to stand in the accelerated weathering machine (SUV) for 1,000 hours, gloss retention ratio was measured and evaluated as follows.

[0144] When the gloss retention ratio is not less than 80 %, from 60 to 80 % and not more than 60 %, weather resistance is evaluated as O, Δ and ×, respectively.

[0145] Alkali resistance: A coated plate obtained in the same manner as in the weather resistance test was dipped in an aqueous solution of 3 % NaOH at 50°C for one week, and coloration and blister of a coating was judged with naked eyes.

[0146] Acid resistance: A coated plate obtained in the same manner as in the weather resistance test was dipped in a 1 % acid solution at 50°C for one week, and coloration and blister of a coating was judged with naked eyes.

[0147] The results are shown in Table 3.

Examples 15 to 17

[0148] An aqueous dispersion of a VdF seed polymer of the present invention was prepared in the same manner as in Example 14 except that the seed polymerization conditions shown in Table 3 were employed, and the same tests as in Example 14 were carried out in the same manner as in Example 14. The results are shown in Table 3.

Comparative Examples 7 and 8

[0149] An aqueous dispersion of a VdF seed polymer was prepared in the same manner as in Example 14 except that the seed polymerization conditions shown in Table 3 were employed, and the same tests as in Example 14 were carried out in the same manner as in Example 14. The results are shown in Table 3.

Table 3

Conditions for seed polymerization							
Kind of aqueous dispersion used		Aqueous dispersion obtained in Example 7	Aqueous dispersion obtained in Example 9	Aqueous dispersion obtained in Example 13	Aqueous dispersion obtained in Example 12	Aqueous dispersion obtained in Comparative Example 2	Aqueous dispersion obtained in Comparative Example 4
Amount used (g)		70	70	70	70	70	70
MMA (g)		11.2	12.0	12.6	9.6	10.4	11.6
PME400 (g)		1.5	1.6	1.7	1.3	1.4	1.6
Tests							
Solid content (% by weight)		42.8	45.9	47.8	38.6	41.1	44.2
Viscosity (CP)		56	100	110	68	10	83
Average particle size (nm)		136.3	120.5	126.1	60.2	277.9	87.3
Minimum film forming temperature (°C)		43	42	39	36	59	47
Transparency		○	○	○	○	△	×
Water absorption ratio (%)		1.8	2.3	3.2	1.5	13.7	24.6
Elution ratio (%)		0.5	0.3	0.3	0.2	2.6	8.3
Gloss (60° G)		75	78	76	78	56	32
Weather resistance		○	○	○	○	○	△
Acid resistance		Not abnormal	Not abnormal	Not abnormal	Not abnormal	Not abnormal	Not abnormal
Alkali resistance		Not abnormal	Not abnormal	Not abnormal	Not abnormal	Slight blister	Blister, coloration

[0150] As is clear from Table 3, when only an ammonium salt of perfluorooctanoic acid which is not reactive is used as an emulsifying agent, if a small amount thereof is used, the particle size becomes large and a highly glossy coating cannot be obtained and if a large amount is used, transparency of the formed film is lowered, and no gloss of the coating is obtained. Also lowering of water resistance and weather resistance of the coating is observed.

[0151] On the contrary, when the reactive emulsifying agent is used according to the present invention, not only any of the above-mentioned properties is satisfied but also a coating of a dispersed aqueous composition having a low MFT even in case of the same resin composition can be obtained.

INDUSTRIAL APPLICABILITY

[0152] The aqueous dispersion of the VdF copolymer of the present invention is excellent in stability against sedimentation because an average particle size of the VdF copolymer in the dispersion is as small as not more than 200 nm and a solid content in the dispersion is as high as from 30 to 60 %.

[0153] Also the process for preparation of the aqueous dispersion of the VdF copolymer of the present invention can provide the above-mentioned dispersion by copolymerizing VdF monomer with the reactive emulsifying agent, in which the dispersion is excellent in stability against sedimentation because an average particle size of the VdF copolymer is as small as not more than 200 nm and a solid content of the dispersion is as high as from 30 to 60 %.

[0154] Further the aqueous dispersion of the VdF seed polymer of the present invention is excellent in stability against sedimentation because an average particle size of the VdF seed polymer in the dispersion is as small as not more than 250 nm and a solid content of the dispersion is as high as from 30 to 60 %. A film obtained from the dispersion has excellent transparency and good water resistance, and also an aqueous paint obtained from the dispersion is highly glossy and is excellent in weather resistance, acid resistance and alkali resistance.

[0155] Further the process for preparation of the aqueous dispersion of the VdF seed polymer of the present invention can provide the above-mentioned dispersion prepared by seed-polymerizing an ethylenically unsaturated monomer in the presence of the VdF copolymer particles obtained by copolymerizing VdF monomer with the reactive emulsifying agent, in which the dispersion is excellent in stability against sedimentation because an average particle size of the VdF seed polymer in the dispersion is as small as not more than 250 nm and a solid content of the dispersion is as high as from 30 to 60 %.

Claims

1. An aqueous dispersion of a vinylidene fluoride copolymer, **characterized in that** the dispersion has a solid content of 30 to 60 % by weight and an average particle size of the copolymer of not more than 200 nm; the copolymer being prepared by copolymerizing vinylidene fluoride monomer with at least one reactive emulsifying agent selected from the group consisting of those represented by the formula (I):




wherein a is an integer of 1 to 10, Y is SO₃M or COOM, M is H, NH₄ or an alkali metal, the formula (II):




wherein X is F or CF₃, b is an integer of 1 to 5, Y is SO₃M or COOM, M is H, NH₄ or an alkali metal, the formula (III):




wherein X is F or CF₃, c is an integer of 1 to 10, Y is SO₃M or COOM, M is H, NH₄ or an alkali metal, the formula (IV):



wherein X is F or CF₃, d is an integer of 1 to 10, Y is SO₃M or COOM, M is H, NH₄ or an alkali metal, the formula (V):



wherein e is 0 or an integer of 1 to 10, Y is SO₃M or COOM, M is H, NH₄ or an alkali metal, and the formula (VI):



wherein f is an integer of 1 to 10, Y is SO₃M or COOM, M is H, NH₄ or an alkali metal.

2. An aqueous dispersion of a vinylidene fluoride seed polymer prepared by emulsion polymerizing a fluorine-free ethylenically unsaturated monomer in the presence of vinylidene fluoride copolymer particles, **characterized in that** the vinylidene fluoride copolymer is a copolymer prepared by copolymerizing vinylidene fluoride monomer with at least one reactive emulsifying agent selected from the group consisting of those represented by the formula (I):




wherein a is an integer of 1 to 10, Y is SO₃M or COOM, M is H, NH₄ or an alkali metal, the formula (II):



wherein X is F or CF₃, b is an integer of 1 to 5, Y is SO₃M or COOM, M is H, NH₄ or an alkali metal, the formula (III):




wherein X is F or CF₃, c is an integer of 1 to 10, Y is SO₃M or COOM, M is H, NH₄ or an alkali metal, the formula (IV):




wherein X is F or CF₃, d is an integer of 1 to 10, Y is SO₃M or COOM, M is H, NH₄ or an alkali metal,

the formula (V):



wherein e is 0 or an integer of 1 to 10, Y is SO_3M or COOM , M is H, NH_4 or an alkali metal, and the formula (VI):



wherein f is an integer of 1 to 10, Y is SO_3M or COOM , M is H, NH_4 or an alkali metal, and that the dispersion has a solid content of 30 to 60 % by weight and an average particle size of the copolymer of not more than 250 nm.

Patentansprüche

1. Wäßrige Dispersion eines Vinylidenfluoridcopolymers, dadurch gekennzeichnet, daß

die Dispersion einen Feststoffgehalt von 30 bis 60 Gewichts-% und eine mittlere Teilchengröße des Copolymers von nicht mehr als 200 nm aufweist; wobei das Copolymer durch das Copolymerisieren von Vinylidenfluoridmonomer mit mindestens einem reaktiven Emulgierungsmittel hergestellt wird, das aus der Gruppe ausgewählt ist, die aus Verbindungen besteht, durch die Formel (I):



worin a eine ganze Zahl von 1 bis 10 ist, Y für SO_3M oder COOM steht, M für H, NH_4 oder ein Alkalimetall steht, die Formel (II):



worin X für F oder CF_3 steht, b eine ganze Zahl von 1 bis 5 ist, Y für SO_3M oder COOM steht, M für H, NH_4 oder ein Alkalimetall steht, die Formel (III):



worin X für F oder CF_3 steht, c eine ganze Zahl von 1 bis 10 ist, Y für SO_3M oder COOM steht, M für H, NH_4 oder ein Alkalimetall steht, die Formel (IV):



worin X für F oder CF_3 steht, d eine ganze Zahl von 1 bis 10 ist, Y für SO_3M oder COOM steht, M für H, NH_4 oder ein Alkalimetall steht, die Formel (V):



worin e 0 oder eine ganze Zahl von 1 bis 10 ist, Y für SO₃M oder COOM steht, M für H, NH₄ oder ein Alkalimetall steht, und die Formel (VI) wiedergegeben werden:



worin f eine ganze Zahl von 1 bis 10 ist, Y für SO₃M oder COOM steht, M für H, NH₄ oder ein Alkalimetall steht.

2. Wäßrige Dispersion eines Vinylidenfluorid-Keimpolymers, die durch die Emulsionspolymerisation eines fluorfreien ethylenisch ungesättigten Monomers in Gegenwart von Vinylidenfluoridcopolymereteilchen hergestellt wird, **dadurch gekennzeichnet, daß** das Vinylidenfluoridcopolymer ein Copolymer ist, das durch die Copolymerisierung von Vinylidenfluoridmonomer mit mindestens einem reaktiven Emulgierungsmittel hergestellt wird, das aus der Gruppe ausgewählt ist, die aus den Verbindungen besteht, die durch die Formel (I):



worin a eine ganze Zahl von 1 bis 10 ist, Y für SO₃M oder COOM steht, M für H, NH₄ oder ein Alkalimetall steht, die Formel (II):



worin X für F oder CF₃ steht, b eine ganze Zahl von 1 bis 5 ist, Y für SO₃M oder COOM steht, M für H, NH₄ oder ein Alkalimetall steht, die Formel (III):




worin X für F oder CF₃ steht, c eine ganze Zahl von 1 bis 10 ist, Y für SO₃M oder COOM steht, M für H, NH₄ oder ein Alkalimetall steht, die Formel (IV):



worin X für F oder CF₃ steht, d eine ganze Zahl von 1 bis 10 ist, Y für SO₃M oder COOM steht, M für H, NH₄ oder ein Alkalimetall steht, die Formel (V):



worin e 0 oder eine ganze Zahl von 1 bis 10 ist, Y für SO₃M oder COOM steht, M für H, NH₄ oder ein Alkalimetall steht, und die Formel (VI) wiedergegeben werden:



worin f eine ganze Zahl von 1 bis 10 ist, Y für SO₃M oder COOM steht, M für H, NH₄ oder ein Alkalimetall steht, und daß die Dispersion einen Feststoffgehalt von 30 bis 60 Gewichts-% und eine mittlere Teilchengröße des Copolymers von nicht mehr als 250 nm aufweist.

Revendications

1. Dispersion aqueuse d'un copolymère de fluorure de vinylidène, **caractérisé en ce que** la dispersion a une teneur en solides de 30 à 60% en poids et une taille particulaire moyenne du copolymère non supérieure à 200 nm ; le copolymère étant préparé en copolymérisant le monomère de fluorure de vinylidène avec au moins un agent émulsifiant réactif choisi dans le groupe constitué par ceux représentés par la formule (I) :



dans laquelle a est un nombre entier de 1 à 10, Y est SO_3M ou COOM , M est H, NH_4 ou un métal alcalin, la formule (II) :



dans laquelle X est F ou CF_3 , b est un nombre entier de 1 à 5, Y est SO_3M ou COOM , M est H, NH_4 ou un métal alcalin, la formule (III) :



dans laquelle X est F ou CF_3 , c est un nombre entier de 1 à 10, Y est SO_3M ou COOM , M est H, NH_4 ou un métal alcalin, la formule (IV) :



dans laquelle X est F ou CF_3 , d est un nombre entier de 1 à 10, Y est SO_3M ou COOM , M est H, NH_4 ou un métal alcalin, la formule (V) :




dans laquelle e vaut 0 ou est un nombre entier de 1 à 10, Y est SO_3M ou COOM , M est H, NH_4 ou un métal alcalin, et la formule (VI) :




dans laquelle f est un nombre entier de 1 à 10, Y est SO_3M ou COOM , M est H, NH_4 ou un métal alcalin.

2. Dispersion aqueuse d'un polymère ensemencé de fluorure de vinylidène préparé par polymérisation en émulsion d'un monomère insaturé éthyléniquement exempt de fluor en présence de particules de copolymère de fluorure de vinylidène, **caractérisé en ce que** le copolymère de fluorure de vinylidène est un copolymère préparé en copolymérisant un monomère de fluorure de vinylidène avec au moins un agent émulsifiant choisi dans le groupe constitué par ceux représentés par la formule (I) :




dans laquelle a est un nombre entier de 1 à 10, Y est SO_3M ou COOM , M est H, NH_4 ou un métal alcalin, la formule (II) :



dans laquelle X est F ou CF_3 , b est un nombre entier de 1 à 5, Y est SO_3M ou COOM , M est H, NH_4 ou un métal alcalin,
la formule (III) :




dans laquelle X est F ou CF_3 , c est un nombre entier de 1 à 10, Y est SO_3M ou COOM , M est H, NH_4 ou un métal alcalin,
la formule (IV) :



dans laquelle X est F ou CF_3 , d est un nombre entier de 1 à 10, Y est SO_3M ou COOM , M est H, NH_4 ou un métal alcalin,
la formule (V) :



dans laquelle e vaut 0 ou est un nombre entier de 1 à 10, Y est SO_3M ou COOM , M est H, NH_4 ou un métal alcalin, et
la formule (VI) :



dans laquelle f est un nombre entier de 1 à 10, Y est SO_3M ou COOM , M est H, NH_4 ou un métal alcalin,
et en ce que la dispersion a une teneur en solides de 30 à 60% en poids et une taille particulaire moyenne du copolymère non supérieure à 250 nm.

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☒ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.